

GRANEL

mai/2024


Dia	Composição Química				Resistência a Compressão			Finura				Expansibilidade	Pega		Consist.
	P. Fogo (%)	RI (%)	SO3 (%)	CaO Livre (%)	03 Dias MPa	07 Dias MPa	28 Dias MPa	Massa Espec. (g/cm³)	Blaine (m²/Kg)	# 325 (%)	# 200 (%)	Quente (mm)	Início (min)	Fim (min)	Normal (%)
1	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
2	2,36	0,36	1,62	0,74	22,8			3,01	5345	0,8	0,2	0,0	178	190	30,4
3	1,99	0,27	1,58	0,71				3,00	5135	0,8	0,2	0,0	170	185	30,4
4	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
5	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---
6								3,01	5367	0,8	0,2	0,0	175	213	30,2
7															
8															
9															
10															
11															
12															
13															
14															
15															
16															
17															
18															
19															
20															
21															
22															
23															
24															
25															
26															
27															
28															
29															
30															
31															

Controle Estatístico

	R3	R7	R28												
MÉDIA	2,18	0,32	1,60	0,73	22,8	#DIV/0!	#DIV/0!	3,01	5282	0,8	0,2	0,00	174	196	30,3
DESVIO	0,26	0,06	0,03	0,02	#DIV/0!	#DIV/0!	#DIV/0!	0,01	128,07	0,00	0,00	0,00	4,04	14,93	0,12
ABNT	≤6,5	≤ 5,0	≤ 4,5		≥ 12,0	≥ 23,0	≥ 40,0					≤ 5	≥ 60	≤ 720	

(\*) Amostra reanalisada

COMPARATIVO ABNT X MIZU



*[Assinatura]*

Lider de Fábrica  
Rogério Americano Alves

*[Assinatura]*

Responsável Técnica  
Jessica Mouta Guimarães  
CRQ:03426796 - 3ª Região